Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1-3. (Canceled)

4. (Currently amended) A plasma display panel, comprising:

a first substrate;

a plurality of first electrodes provided on the first substrate;

a plurality of second

~~arranged with having a first and a second sustain~~ electrodes ~~form a pair on an upper substrate;~~

~~a plurality of data electrodes arranged on a lower substrate to cross the electrodes;~~

~~a plurality of barrier ribs arranged in parallel to the data electrodes with a designated gap to form a discharge space between the upper substrate and the lower substrate;~~

~~and~~

~~a plurality of phosphorus layers having a red phosphorus layer, a green phosphorus layer and a blue phosphorus layer which are formed along the inner wall of the barrier ribs;~~

~~and~~

~~wherein the green phosphorus layer is made of Zn_2SiO_4:Mn phosphor, YBO_3:Tb phosphor and BaAl12019:Mn phosphor, and the mixing rate of BaAl12019:Mn phosphor to the total weight is 1~25 wt%~~ provided on the first substrate, the first and second electrodes being provided in a first direction;

a second substrate;

a plurality of address electrodes provided on the second substrate in a second direction, the first direction being different from the second direction;

a plurality of barrier ribs provided on the second substrate in the second direction;

a plurality of discharge cells, each cell provided between two adjacent barrier ribs, and having corresponding first, second and address electrodes;

a green phosphor material provided to a first prescribed number of discharge cells;

a red phosphor material provided to a second prescribed number of discharge cells; and

a blue phosphor material provided to a third prescribed number of discharge cells, wherein the green phosphor material comprises a first class phosphor material of Zn_2SiO_4:Mn,

and at least one of a second class phosphor material or a third class phosphor material,

the second class phosphor material comprising at least one of $LaPO_4$:Tb, $Y_3Al_3(BO_3)_4$Tb, Y(Al, Ga)5012:Tb, YBO_3:Tb, or (Y, Gd)BO_3:Tb, and

the third class phosphor material comprising at least one of BaAl12019:Mn,

BaAl14023:Mn, or Ba(Sr,Ma)AlO:Mn, and wherein

weight of the first class phosphor material to total weight is less than 100%.

5-18. (Canceled).

19. (New) The plasma display panel of claim 4, wherein the second class phosphor material comprises Zn_2SilO_4:Mn, (Y, Gd)BO_3:Tb, and the third class phosphor material comprises BaAl12019:Mn.

20. (New) The plasma display panel of claim 4, wherein the third class phosphor material to the total weight is 1~25 wt%.

21. (New) The plasma display panel of claim 19, wherein the third class phosphor material to the total weight is 1~25 wt%.

22. (New) The plasma display panel of claim 4, wherein the second class phosphor to the first class phosphor is 25~80 wt%.

23. (New) The plasma display panel of claim 19, wherein the second class phosphor to the first class phosphor is 25~80 wt%.

24. (New) The plasma display panel of claim 22, wherein the third class phosphor to the total weight is 1~25 wt%.

25. (New) The plasma display panel of claim 23, wherein the third class phosphor to the total weight is 1~25 wt%.

26. (New) A plasma display panel comprising:

a first substrate;

a plurality of first electrodes provided on the first substrate;

a plurality of second electrodes provided on the first substrate, the first and second electrodes being provided in a first direction;

a second substrate;

a plurality of address electrodes provided on the second substrate in a second direction, the first direction being different from the second direction;

a plurality of barrier ribs provided on the second substrate in the second direction;

a plurality of discharge cells, each cell provided between two adjacent barrier ribs, and having corresponding first, second and address electrodes;

a green phosphor material provided to a first prescribed number of discharge cells;

a red phosphor material provided to a second prescribed number of discharge cells; and

a blue phosphor material provided to a third prescribed number of discharge cells,

wherein the green phosphor material comprises a first class phosphor material of Zn_2SiO_4:Mn, and a second class phosphor material comprising at least one of $LaPO_4$:Tb, $Y_3Al_3(BO_3)_4$Tb, Y(Al, Ga)5012:Tb, YBO_3:Tb, or (Y, Gd)BO_3:Tb.

27. (New) The plasma display panel of claim 26, wherein the mixing rate of the second class phosphor to the first class phosphor is 25~50 wt%.

28. (New) The plasma display panel of claim 26, wherein the green phosphor material comprises Zn_2SiO_4:Mn and (Y, Gd)BO_3:Tb or Zn_2SiO_4:Mn and $Y_3Al_3(BO_3)_4$Tb.

29. (New) The plasma display panel of claim 28, wherein (Y, Gd)BO_3:Tb and $Y_3Al_3(BO_3)_4$Tb to total weight is 25~50 wt%.

30. (New) A plasma display panel comprising:

a first substrate;

a plurality of first electrodes provided on the first substrate;

a plurality of second electrodes provided on the first substrate, the first and second electrodes being provided in a first direction;

a second substrate;

a plurality of address electrodes provided on the second substrate in a second direction, the first direction being different from the second direction;

a plurality of barrier ribs provided on the second substrate in the second direction;

a plurality of discharge cells, each cell provided between two adjacent barrier ribs, and having corresponding first, second and address electrodes;

a green phosphor material provided to a first prescribed number of discharge cells;

a red phosphor material provided to a second prescribed number of discharge cells; and

a blue phosphor material provided to a third prescribed number of discharge cells, wherein the green phosphor material comprises a first class phosphor material of Zn_2SilO_4:Mn, and a second class phosphor material comprising at least one of $LaPO_4$:Tb, $Y_3Al_3(BO_3)_4$Tb, Y(Al, Ga)5012:Tb, YBO_3:Tb, or (Y, Gd)BO_3:Tb, and a third phosphor material comprising at least one of BaAl12019:Mn, BaAl14023:Mn, or Ba(Sr,Ma)AlO:Mn.

31. (New) The plasma display panel of claim 30, wherein the second class phosphor material comprises (Y, Gd)BO_3:Tb or $Y_3Al_3(BO_3)_4$Tb;

and the third class phosphor material comprises BaAl12019:Mn.

32. (New) The plasma display panel of claim 30, wherein the third class phosphor material to the total weight is 1~25 wt%.

33. (New) The plasma display panel of claim 31, wherein the third class phosphor material to the total weight is 1~25 wt%.

34. (New) The plasma display panel of claim 30, wherein the second class phosphor to the first class phosphor is 25~80 wt%.

35. (New) The plasma display panel of claim 31, wherein the second class phosphor to the first class phosphor is 25~80 wt%.